



Consumer Products Services Division  
 100 Northpointe Parkway  
 Buffalo, NY 14228

Technical Report: (5112) 108-0017

April 23, 2012

Sample: DECKadence® Marine Flooring

Coefficient Test

Evaluation	Citation Method	Samples	Criteria	Results	Rating
Skid Resistance	ASTM F609-05	1	Coefficient of static friction 1 Min.	Glazed Porcelain: 1.03 Ceramic: 1.16 Plexiglas: 1.62	PASS PASS PASS

Neither DECKadence Marine nor its contributors shall be held liable for any of the information herein described and/or contained and assumes no responsibility for third-party usage of the information. In no event shall DECKadence Marine or its contributors be liable for any direct, indirect, incidental, special, exemplary, or consequential damages, however caused and/or on any theory of liability, whether in contract, strict liability, (including negligence or otherwise) arising in any way out of the use of this information.